ชื่อเรื่อง คุณสมบัติทางกายภาพและเคมีของถ่านกัมมันต์จากไม้ทานาคาที่

ผ่านการกระตุ้นด้วยกรดฟอสฟอริก

ผู้วิจัย รัชฎาภรณ์ ชมสวนสวรรค์

อาจารย์ที่ปรึกษา ผู้ช่วยศาสตราจารย์ ดร.นวลกมล อาภรณ์พงษ์

อาจารย์ที่ปรึกษาร่วม อาจารย์ ดร.ชาญยุทธ กฤตสุนันท์กุล

ประเภทสารนิพนธ์ วิทยานิพนธ์ปริญญาตรี วท.บ. สาขาวิชาทรัพยากรธรรมชาติและ

สิ่งแวดล้อม,

มหาวิทยาลัยนเรศวร, 2563

คำสำคัญ ถ่านกัมมันต์ ไม้ทานาคา กรดฟอสฟอริก

บทคัดย่อ

งานวิจัยนี้มีจุดประสงค์เพื่อศึกษาคุณสมบัติทางกายภาพและทางเคมีของถ่านกัมมันต์จากไม้ ทานาคาที่ผ่านการกระตุ้นด้วยกรดฟอสฟอริก จากการเตรียมถ่านคาร์บอในซ์จากไม้ทานาคา ผล การศึกษาพบว่า อุณหภูมิที่เหมาะสมในการเผาคาร์บอในซ์คือที่อุณหภูมิ 600°C เป็นเวลา 1 hr ให้ ผลผลิตของถ่านเท่ากับ 22.27% การกระตุ้นด้วยกรดฟอสฟอริกที่อัตราส่วนระหว่างถ่านคาร์บอในซ์ ต่อกรดฟอสฟอริกเท่ากับ 1:3 g:ml และเผากระตุ้นอีกครั้งที่อุณหภูมิ 700°C เป็นเวลา 1 hr โดย ถ่านกัมมันต์ที่ผลิตได้จะมีค่าการดูดซับไอโอดีนและเมทิสันบลูสูงสุดเท่ากับ 650.14 และ71.63 mg/g ตามลำดับ ผลการศึกษาลักษณะทางกายภาพและทางเคมีพบว่า ถ่านคาร์บอในซ์จากไม้ทานาคามี ปริมาณธาตุองค์ประกอบของธาตุแคลเซียม (54.05%wt.) โพแทสเซียม (21.22%wt.) ฟอสฟอรัส (9.49%wt.) และแมกนีเซียม (6.38%wt.) และมีประจุบนพื้นผิวเป็นลบ จากการศึกษาประสิทธิภาพ ในการดูดซับไอโอดีนในน้ำ พบว่า ถ่านกัมมันต์จากไม้ทานาคามีประสิทธิภาพในการดูดซับสูงสุด 85.20% นอกจากนั้นพบว่าถ่านกัมมันต์จากไม้ทานาคาและถ่านกัมมันต์เกรดการค้ามีประสิทธิภาพใน การดูดซับเมทิสันบลูไม่แตกต่างกัน ดังนั้น จากการศึกษาคุณสมบัติของไม้ทานาคาที่เป็นไม้ท้องถิ่นใน จังหวัดตากพบว่ามีศักยภาพในการนำมาผลิตเป็นถ่านกัมมันต์เพื่อเพิ่มคุณค่าทางเศรษฐกิจให้กับคนใน ท้องถิ่นได้

Title Physical and Chemical Properties of Activated Carbon from

Thanaka Wood Using H₃PO₄ Activation

Author Rutchadaporn Chomsuansawan

Advisor Asst.Prof.Dr. Noulkamol Arpornpong, Ph.D

Co - Advisor Dr. Chanyut Krittasunankun, Ph.D..

Academic Paper Undergraduate Thesis B.Sc. in Natural Resources and

Environment,

Naresuan University, 2020

Keywords Activated carbon, Thanaka wood, Phosphoric acid

ABSTRACT

The purpose of this research is to study the physical and chemical properties of activated carbon from Thanaka wood using H₃PO₄ activation. From the carbonized process of the Tanaka wood, the results showed that the optimum carbonization temperature was at 600°C for 1 hr with providing 22.27% charcoal yield. The activated carbon had the highest Iodine and Methylene blue adsorption capacity was 650.14 and 71.63 mg/g, respectively when it was activated with phosphoric acid at the ratio of charcoal (g) to phosphoric acid (mL) of 1:3 at 700°C for 1 hr. The study of physical and chemical characteristics found that the carbonized charcoal from Tanaka wood consisting of calcium (54.05% wt.), potassium (21.22% wt.), phosphorus (9.49% wt.), and magnesium (6.38% wt.), has the negative surface charge. From the study of lodine adsorption efficiency in water, it was found that the activated carbon from the Thanaka wood had the highest absorption efficiency of 85.20%. Moreover, the activated carbon from the Thanaka wood had the methylene blue absorption efficiency as the same as the commercial activated charcoal. Therefore, from the properties of the Thanaka wood, a local wood in Tak province, it was found that it has the potential to be used as activated carbon to increase the economic value of the local people.